

Description

Polyisocyanurate rigid foam

Blowing agents:

CFCs/HCFCs-free

Approvals, Homologations, Compliances

ASTM C591 - Type II Grade 2

Characteristics

Color			Green
Nominal density	ASTM D1622/EN 1602/ EN ISO 845	lb/ft ³ (kg/m ³)	2.5 (40)
Compressive resistance – Parallel (74°F/23°C)	ASTM D1621/EN 826	psi (MPa)	45 (0.309)
Compressive resistance - Perpendicular (74°F/23°C)	ASTM D1621/EN 826	psi (MPa)	31 (0.213)
Tensile strength - Parallel (74°F/23°C)	ASTM D1623-A/EN 1607	psi (MPa)	63 (0.435)
Tensile strength - Perpendicular (74°F/23°C)	ASTM D1623-A/EN 1607	psi (MPa)	49 (0.340)
Shear strength - Perpendicular (74°F/23°C)	ASTM C273/EN 12090	psi (MPa)	28 (0.195)
Thermal conductivity - Initial (75°F/24°C)	ASTM C518/EN 12667	BTU-in/hr-ft ² ·°F (mW/mK)	0.159 (22.8)
Thermal conductivity - 180 days (75°F/24°C)	ASTM C518/EN 12667	BTU-in/hr-ft ² ·°F (mW/mK)	0.183 (26.0)
Surface burning characteristics	ASTM E84	FSI	<25
Surface burning characteristics	ASTM E84	Smoke Dev.	<450
Dimensional stability (-40°F/-40°C, 7 days) - linear change (length)	ASTM D2126/EN 1604	%	0.5
Dimensional stability (+212°F/+100°C, 7 days) - Linear change (length)	ASTM D2126/EN 1604	%	1.0
Dimensional stability (+158°F/70°C, 97% R.H., 7 days) - Linear change (length)	ASTM D2126/EN 1604	%	±1.5
Water vapor permeability (74°F/23°C, 50% R.H.)	ASTM E96/EN 12086	Perm-inch (ng/s·m·Pa)	3.5
Water absorption by volume	ASTM C272	%	<0.5
Operating temperature		°F (°C)	-320/+300 (-196/+149)
R-Value - 180 days, 1 inch (75°F/24°C)	ASTM C518/EN 12667	hr-ft ² ·°F/BTU (m ² ·K/W)	5.46 (0.97)
Closed-cell content	ASTM D6226/EN ISO 4590	%	>92
Hot-Surface Performance (300°F/149°C)	ASTM C411		Pass

Handling notice

Terms "parallel" and "perpendicular" are referred to slab/specimen/block thickness direction.

DUNA-USA INC. - Headquarters: 4210 FM 1405 - Baytown, TX 77523 - Ph: 281-383-3862 - Fax: 281-383-0115

Michigan plant: 5900 West 6th street, Ludington, MI 49431

Web: www.dunagroup.com/usa/home - Email: info-dunausa@dunagroup.com



Above 300°F, discoloration and surface carbonization will occur, involving possible changes of the physical and mechanical properties of the material.

In some applications polyurethane may present fire risks, e.g. if exposed to fire or to excessive heat in presence of oxygen or air, including when welding or cutting with torches.

It is the Customer's responsibility to determine if product described herein is appropriate for Customer's purposes and end-use and to ensure that working place, storage and disposal practices are in compliance with any applicable law.

Remarks

For usage information, personal protective equipment, transport, storage and disposal of waste it is essential to refer to the Material Safety Data Sheets.

Values shown are determined from laboratory tests and obtained under controlled conditions; they outline typical characteristics and they do not constitute anyhow a sales specification; they are based on DUNA-USA's current knowledge and experience of the products when properly stored, handled and applied in accordance with our recommendations.

This Technical Data Sheet cancels and replaces any other previous issue.

DUNA-USA does not accept responsibility for incorrect use of its products as it cannot ensure the correct methods of application have been followed; we therefore specifically disclaim any liability for consequential or incidental damages of any kind, including lost profits.

DUNA-USA reserves the right to change the data in this information sheet without any prior notice.
